



熠本新材料（中山）有限公司
EEBEN TEX Report

08 日 / Date 03 月 / Month 2022 年 / Years

全國免費諮詢 400 8273 299
National Toll Free

標準品 Standard sample	AST-202 高牢度中黃			批 號 Lot No :	标准样		
樣 品 Test samples	AST-202 高牢度中黃			批 號 Lot No :	CM22030601		
對比測試 Comparison test	標準品 Standard sample	樣 品 Test samples	批次數量 Production	2000 KG	遷移/升華 Migrate/Sublimation	☒ OK ☐ NO	
顏料含量 Pigment content	30.5 %	30.5 %	測試標準 Test Standards	ISO ☒ AATCC ☐ JIS ☐	高溫拔印 Discharge	-- 級Rating	
塗料含固量 Pigment content	50 %	50 %	測色標準 color of Standard	1.Batch colour CIE15. 2 ☐ 2.目測 Visual ☐	環境溫度 Storage temperature	0-40 °C	
色漿粘度 Viscosity	2000 mPa·s	2300 mPa·s	對色光源 Light source	D65 ☒ F ☐ A ☐ UV ☐	擴邊滲色 Bleeding	加水枕標 ☐ OK ☐ NO water Wipe 彩色對標 ☐ OK ☐ NO Color on the pressure	
PH值 PH value	7±1	7.3	着色力 Coloring	同等	☐ 甲醛Formaldehyde ☐ 偶氮AZO ☐ APEO ☐ 重金屬Metal		
粒徑大小 Particle size	μm	μm	色相差距 Color	DI: Da: 相同 Db: De:	✓ 表示通過環保國際認證 That environmental protection through international certification ✗ 表示環保數據超標，具體看檢測報告 That excessive environmental data. Please see the specific monitoring report.		
↓標準品 Standard sample		5%	↓樣 品 Test samples	↓標準品 Standard sample			0.5%
☒ 檢測合格，同意生產 Of qualified, agreed to produce ☐ 檢驗差距過大，要求退貨 The test gap is too large, and demands the return of ☐ 測試中濃度或色光有2%左右差異，請上級批示處理 Concentration or color card is a little difference in the test, a higher grant deals 備注: Remarks							
技術部: 江紹棟 Technonlogy				QC: 柯賢女			



熠本新材料中山有限公司
EEBEN New Material (zhongshan) CO.,Ltd
www.jmyiben.com